

ADAPTOR 25-27mm

(ABS005-1)

Connects two pieces of aspirating smoke detection pipe of different sizes 25mm to 27mm (Visa Versa). This devise is designed for aspirating fire detection only.

Installation Instructions:


Use the correct solvent Plusbon 3019.


Do not paint.


Keep pipe clean and free from dust.

Keep pipe clean and free from dust.
Do not install in direct sunlight.
Only install with approved pipe.
Do not use solvents to clean,
only soapy water.


Part No. ABS005-1
Pipe colour RED
Diameter Tolerance +/- 0.15mm












Front Elevation



RAW MATERIAL DATA

Kumho ABS 750

Acrylonitrile Butaduene Styrene

Pysical

Specific Gravity 1.04
Test Method ASTM D792

Melt Mass - Flow Rate (MFR) 200°C/21.6 kg 47 g/10 min 200°C/5.0 kg 4.1 g/10 min 220°C/10.0 kg 34 g/10 min Test Method ASTM D1238

Molding Shrinkage -Flow 0.0040 to 0.0070 in/in Test Method ASTM D955

Mechanical:

Tensile Strength Yield, 73°F (23°C) 1.97 in (50.0mm) 6670 psi Test Method ASTM D638

Tensile Elongation

Yield, 73°F (23°C) 1.97 in (50.0 mm), 15% Test Method ASTM D638

Flexural Modulus

Yield, 73°F (23°C) 0.118 in (3.00 mm) 312000 psi Test Method ASTM D638

Flexural Strength

Yield, 73°F (23°C) 0.118 in (3.00 mm) 9230 psi Test Method ASTM D790

Impact

Noched Izod Impact 73°F(23°C), 0.126 in (3.20 mm), 5.5 ft·lb/ir 73°F(23°C), 0.252 in (6.40 mm), 4.8 ft·lb/ir Test Method ASTM D256

Hardnes

Rockwell Hardness (R-Scale) 108 Test Method ASTM D785

Thermal

Deflection Temperature Under Load 264 psi (1.8 MPa), Unanneald 185°F/85°C Test Method ASTM D648

Vicat Softening Temperature 203°F/95°C Test Method ASTM D1525

Flamibility

Flame Rating 0.0630 in (1.60 mm) HB 0.0866 in (2.20 mm) HB 0.126 in (3.20 mm) HB

0.126 in (3.20 mm) HB Test Method UL 94

Fire Suppression Limited
Unit 11, Eldonwall Trading Estate,
St.Phillips, Bristol, BS4 3QQ

Tel: 0845-127-9915 Fax: 0845-127-9959 sales@firesuppression.co.uk