

FLUSH SAMPLING KIT

(ABSG019F - 25mm)


Used when the aspirating pipework is above a suspended ceiling, the flush head is fixed to the ceiling tile with the supplied nut and linked to the pipework using a two meter length of 10mm OD tubing and a capillary T piece which links into the pipe.

Installation Instructions:

Use the correct solvent Plusbond 3019. Do not paint.

Keep pipe clean and free from dust.
Do not install in direct sunlight.
Only install with approved pipe.
Do not use solvents to clean,
only soapy water.

Part No. ABSG019F
Fitting colour GREY
Diameter Tolerance +/- 0.15mm



RAW MATERIAL DATA

Kumho ABS 750

Acrylonitrile Butaduene Styrene

Pysical

Specific Gravity 1.04
Test Method ASTM D792

Melt Mass - Flow Rate (MFR) 200°C/21.6 kg 47 g/10 min 200°C/5.0 kg 4.1 g/10 min 220°C/10.0 kg 34 g/10 min Test Method ASTM D1238

Molding Shrinkage

Flow 0.0040 to 0.0070 in/in Test Method ASTM D955

Mechanical:

Tensile Strength
Yield, 73°F (23°C)
1.97 in (50.0mm)
6670 psi
Test Method ASTM D638

Tensile Elongation

Yield, 73°F (23°C) 1.97 in (50.0 mm), 15% Test Method ASTM D638

Flexural Modulus

Yield, 73°F (23°C)
0.118 in (3.00 mm)
312000 psi
Test Method ASTM D638

Flexural Strength

Yield, 73°F (23°C)
0.118 in (3.00 mm)
9230 psi
Test Method ASTM D790

Impact

Noched Izod Impact
73°F(23°C), 0.126 in (3.20 mm), 5.5 ft·lb/in
73°F(23°C), 0.252 in (6.40 mm), 4.8 ft·lb/in
Test Method ASTM D256

<u>Hardness</u>

Rockwell Hardness (R-Scale) 108 Test Method ASTM D785

Thermal

Deflection Temperature Under Load
264 psi (1.8 MPa), Unanneald 185°F/85°C
Test Method ASTM D648

Vicat Softening Temperature 203°F/95°C Test Method ASTM D1525

Flamibility

Flame Rating
0.0630 in (1.60 mm) HB
0.0866 in (2.20 mm) HB
0.126 in (3.20 mm) HB
Test Method UL 94

RAW MATERIAL DATA

Nylo

NFM 10x7.5 -OD Tol's +0.03/-0.09mm Burst Pressure 995 PSI / 68 bar Bend Radius 40mm Weight/30m 1.08kgs

NEM 10x8 -OD Tol's +0.02/-0.10mm Burst Pressure 772 PSI / 53 bar Bend Radius 50mm Weight/30m 0.87kgs

Temperature Range --40°C to +70°C, Occasional use up to +130°C, Brittle point: -70°C

Technical information for use as a guide only.

Pressure values given are based on the short term burst pressure at 20°C based on a 3:1 safety factor. Any increase in temperature above 20°C will result in a decline in working pressure values.

Products and specifications are subject to improvements and change without notice.

Fire Suppression Limited
Unit 11, Eldonwall Trading Estate,
St.Phillips, Bristol, BS4 3QQ

Tel: 0845-127-9915 Fax: 0845-127-9959 sales@firesuppression.co.uk

©All rights reserved. Fire Suppression Ltd.